










Cinq - Technical information

Tile collection performance based on industry standards.

Technical Information			8 x 10 in / 19.9 x 24.9 cm MATTE GLAZED CERAMIC	13 x 13 in / 32.8 x 32.8 cm MATTE GLAZED PORCELAIN
	WATER ABSORPTION	ANSI / ISO - (%)	10% ≤ E ≤ 16% - P4	< 0.5%
	ABRASION RESISTANCE	ANSI / ISO	CLASS 0	CLASS 3
	SCRATCH HARDNESS	ANSI / ISO - (Mohs)	3	6
	BREAKING STRENGTH	ANSI - (lbf) ISO - (N)	>230 ≥1000	≥300 ≥1300
	SHADE VARIATION		V1	
	SLIP RESISTANCE	ANSI - DCOF (WET) ISO - R VALUE	MATTE N/A MATTE N/A	MATTE ≥0.50 MATTE R(-)
	CHEMICAL RESISTANCE	ANSI / ISO	CLASS B	CLASS A
	STAIN RESISTANCE	ANSI / ISO	CLASS B CLASS 4	CLASS A CLASS 5
	FROST RESISTANCE	ANSI / ISO	NOT RESISTANT	PASS

Test values are based on ANSI / ISO standards according to: ANSI A137.1 - Porcelain tile P1 Class, ISO 13006 - G - Bia Group - En 14411 - G - Bia Group.
 Variances in test values can occur in different production lots.
 Test values are based on ANSI / ISO standards according to: ANSI A137.1 Non-Vitreous P4 Class, ISO 13006 - L - Group BIII - EN 14411 - L - Group BIII.
 Variances in test values can occur in different production lots.

Usage recommendations

Anatolia's recommendations for suitable applications.

Usage Recommendations*		MATTE GLAZED CERAMIC		MATTE GLAZED PORCELAIN	
APPLICATION		WALL	FLOOR	WALL	FLOOR
INTERIOR	RESIDENTIAL	•	•	•	•
	COMMERCIAL	•	•	•	•
	HEAVY COMMERCIAL				
EXTERIOR	RESIDENTIAL / COMMERCIAL			•	

* These recommendations are not defined by ANSI/ISO standards.